

Low temperature silver ink

LTS 10

Applications:

Contacts for organic photovoltaic and/or other devices

Processing:

Screen printing

Brushing

Dispensing

Curing temperature: 110...150° C (10....20 min.)

Resistivity: max. 20 mΩ/sq. (25 μ thickness)

Recommended thickness: 10....15 μ